












**GRES PORCELLANATO . PORCELAIN STONEWARE**

## GRÈS CÉRAMÉ . FEINSTEINZEUG

**UNI EN 14411 Bia Allegato G (ISO 13006)**
[www.dadoceramica.it](http://www.dadoceramica.it)

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft		Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	<b>PIETRA DI BALI 15x15 - 31x62</b>
 <b>Lunghezza e larghezza</b> / Lenght and width Longuer et largeur / Länge und breite <b>Spessore</b> / Thickness Epaisseur / Stärke <b>Rettilineità spigoli</b> / Straightness of sides Rectitude des arêtes / Kantengeradheit <b>Ortogonalità</b> / Rectangularity Orthogonalité / Rechtwinkligkeit <b>Planarità</b> / Surface flatness Planeité de surface / Ebenflächigkeit	UNI EN ISO 10545-2	<b>N ≥ 15 cm</b>		<b>Conforme</b> Corresponding Conforme Entsprechend
		<b>%</b>	<b>(mm)</b>	
		± 0,6 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,0 Rect	
		± 5	± 0,5	
		± 0,5 Non Rect. ± 0,3 Rect	± 1,5 Non Rect. ± 0,8 Rect	
± 0,5 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,5 Rect	± 0,5 Non Rect. ± 0,4 Rect	± 2,0 Non Rect. ± 1,8 Rect	
 <b>Qualità della superficie</b> Surface quality Qualités de la surface Oberflächenqualität	UNI EN ISO 10545-2	<b>Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili</b> Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen		<b>Conforme</b> Corresponding Conforme Entsprechend
 <b>Assorbimento d'acqua</b> Water absorption Absorption d'eau Wasseraufnahme	UNI EN ISO 10545-3	$\leq 0,5\%$ <b>Individual max 0,6%</b>		$\leq 0,5\%$
 <b>Sforzo di Rottura</b> / Breaking strength Effort de rupture / Bruchkraft (≥ 7,5 mm thickness) <b>Resistenza alla flessione</b> / Modulus of Rupture Résistance à la flexion / Biegefestigkeit	UNI EN ISO 10545-4	<b>S ≥ 1300 N</b>		<b>S ≥ 1300 N</b>
 <b>Resistenza all'abrasione (metodo PEI)</b> Abrasion resistance (PEI test) Résistance à l'abrasion (méthode PEI) Widerstand gegen Abrieb (nach PEI)	UNI EN ISO 10545-7	<b>Segnala la classe di abrasione e i cicli superati</b> Report abrasion class and cycles passed		<b>Da 2 a 5 in base al colore</b> <b>From 2 to 5, according to color</b>
 <b>Resistenza al gelo</b> Resistance to frost Resistance aux gel Frostbeständigkeit	UNI EN ISO 10545-12	<b>Richiesto</b> Required		<b>Non gelivo</b> Frost-proof Non gélifs Frostsicher
 <b>Resistenza ai prodotti chimici</b> Resistance to chemical products Résistance aux produits chimiques Widerstand gegen Chemikalien	UNI EN ISO 10545-13	<b>Resistenza a basse concentrazioni di acidi e alcali</b> Resistance to low concentrations of acids and alkalis <b>Secondo la classificazione indicata dal fabbricante</b> Manufacturer is to state classification		<b>LA</b>
		<b>Resistenza ad alte concentrazioni di acidi e alcali</b> Resistance to high concentrations of acids and alkalis <b>Metodo di prova disponibile</b> Test method available		<b>HA</b>
		<b>Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina</b> Resistance to household chemicals and swimming pool salt <b>Classe minima B</b> Minimum class B		<b>A</b>
 <b>Resistenza alle macchie</b> Staining resistance Resistance aux taches Widerstand gegen Fleckenbildung	UNI EN ISO 10545-14	<b>Min. 3</b>		<b>Conforme</b> Corresponding Conforme Entsprechend
 <b>Resistenza agli sbalzi termici</b> Thermal shock resistance Resistance aux écarts de température Temperaturwechselbeständigkeit	UNI EN ISO 10545-9	<b>Metodo di prova disponibile</b> Test method available		<b>Resiste</b> Resistant Résiste Widerstandsfähig
<b>Caratteristiche accessorie / Additional features</b>				
 <b>Stabilità dei colori</b> Colours stability Stabilité des couleurs Farbbeständigkeit	DIN 51094	<b>Colorazione Stabile</b> Stable coloring		<b>Conforme</b> Corresponding Conforme Entsprechend
<b>Caratteristiche di sicurezza / Safety characteristics</b>				
 <b>Resistenza allo scivolamento **</b> Slip resistance Résistance au glissement Rutschemmende Eigenchaft	METODO B.C.R.A.	$\mu > 0,40$		<b>Conforme</b> Corresponding Conforme Entsprechend
	DIN EN 51130	<b>Classe dichiarata /Declared Class</b>		<b>R11</b>