

















Dado Ceramica S.r.l.

Via Sicilia 21 - 40017 - San Matteo della Decima (BO) - Italy

Telefono +39 051 6819611 - Telefax +39 051 6819650

 info@dadoceramica.it - Follow us   
RIVESTIMENTI IN PASTA BIANCA . WHITE-BODY WALL TILE
REVÊTEMENTS EN PÂTE BLANCHE . WEISSSCHERBIGE WANDFLIESEN
UNI EN 14411 BIII Allegato L (ISO 13006)

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft	Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	RIVESTIMENTI WALL TILES
---	---------------------------------------	---	-----------------------------------

			N ≥ 15 cm		
			%	(mm)	
 Lunghezza e larghezza / Length and width Longuer et largeur / Länge und breite  Spessore / Thickness Epaisseur / Stärke  Rettilineità degli spigoli Straightness of sides  Ortogonalità / Rectangularity Orthogonalite / Rechtwinkligkeit  Planarità / Surface flatness Planeite de surface / Ebenflächigkeit	UNI EN ISO 10545-2		± 0,6 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,0 Rect	Conforme Corresponding Conforme Entsprechend
			± 10	± 0,5	
			± 0,5 Non Rect. ± 0,3 Rect	± 1,5 Non Rect. ± 0,8 Rect	
			± 0,5 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,5 Rect	
 Qualità della superficie Surface quality Qualités de la surface Oberflächenqualität	UNI EN ISO 10545-2		Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen		Conforme Corresponding Conforme Entsprechend
 Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme	UNI EN ISO 10545-3		> 10 %		Conforme Corresponding Conforme Entsprechend
 Sforzo di rottura Breaking strength Effort de rupture Bruchkraft  Resistenza alla flessione Modulus of rupture Résistance à la flexion Biegefestigkeit	UNI EN ISO 10545-4		Spessore / Thickness ≥ 7,5 Non meno di / Not less than 600 N		> 600 N
			Spessore / Thickness < 7,5 Non meno di / Not less than 200 N		
			Spessore / Thickness ≥ 7,5 Minimo / Minimum 12 N/mm²		> 12 N/mm²
			Spessore / Thickness < 7,5 Minimo / Minimum 15 N/mm²		> 15 N/mm²
 Resistenza al cavillo Crazing resistance Résistance au tressillage Haarißbeständigkeit	UNI EN ISO 10545-11		Richiesta Requested Demandée Gefragt		Conforme Corresponding Conforme Entsprechend
 Resistenza agli sbalzi termici Thermal shock resistance Resistance aux écarts de température Temperaturwechselbeständigkeit	ISO 10545-9		Metodo di prova disponibile Test method available		Resiste Resistant Résiste Widerstandsfähig
 Resistenza agli acidi Chemical resistance Résistance à l'attaque chimique Beständigkeit gegen Chemikalien	UNI EN ISO 10545-13		Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina Resistance to household chemicals and swimming pool salt Classe minima B Minimum class B		A
 Resistenza alle macchie Staining resistance Resistance aux taches Widerstand gegen Fleckenbildung	UNI EN ISO 10545-14		Classe 3 Class 3 Klasse 3		Conforme Corresponding Conforme Entsprechend